

Dyezol

Middle Temperature (60°C) Exhaustion Dyeing Reactive Dyes
中溫型活性染料

DYEZOL Vinyl Sulfone & Different Bifunctional On Cotton Depth of shade 3.0% (o.w.f.) 染色濃度 3.0%		染料索引號 Color Index No.	溶解度 Solubility 80°C (g/L)	耐日光牢度 Fastness to Light / 3% o.w.f.	耐水洗牢度 Fastness to Washing	耐摩擦牢度/乾 Fastness to Rubbing / Dry	耐氯牢度 Fastness to Chlorine / 20 ppm	耐酸汗 Fastness to perspiration / Acid	耐鹼汗 Fastness to perspiration / Alkali
Yellow 4GL		Y-160	80	>6	4-5	4-5	3	5	5
Yellow 3GL		Y-64	80	>6	4-5	4-5	3	5	5
Yellow GR 150%		Y-15	100	5-6	4-5	4-5	2-3	5	5
Yellow 3RS 150%		Y-145	120	6	4	5	4	5	5
Orange 2R		O-122	100	5-6	4-5	4	3-4	4-5	4-5
Orange 3R 135%		O-16	100	5-6	4-5	4-5	3-4	5	5
Scarlet 2GF		R-222	100	4	4-5	4-5	3-4	5	5
Red 2BF		R-194	120	5-6	4-5	4-5	4	4-5	5
Red 3RS 150%		R-195	150	5-6	4-5	4	4-5	5	4-5
Red F3B		R-180	100	4-5	4-5	4	4	4-5	4-5
Red ME6B		R-159	90	4-5	4	3-4	4	4	4
Red RB		R-198	80	5-6	4-5	4-5	3-4	5	4-5
Turq. Blue G 133%		B-21	150	>6	4	4-5	4	4-5	4-5
Blue BB 133%		B-220	100	>6	4-5	4-5	4	4	4
Blue ED-G		B-198.1	100	6-7	5	5	3-4	4-5	4-5
Blue R s/p 150%		B-19	150	>6	4-5	4-5	3-4	5	5
Blue BRF-N 150%		B-221.1	100	5-6	4-5	4-5	3-4	4-5	4-5
Navy Blue BF		B-222	100	4-5	4-5	4-5	4	4	4
Navy Blue FBL		B-222.1	100	4-5	4-5	4-5	4	4	4
Navy Blue GF			100	4.5	4-5	4	3-4	4	4
Black B 150%		Bk-5	150	4-5	4-5	4-5	3	4-5	5
Deep Orange S-4R			100	3-4	5	5	4-5	5	5
Deep Cherry S-D			100	4-5	4-5	5	4-5	4-5	5
Deep Night S-R			100	4	5	5	3-4	5	5
Yellow LX			120	>6	5	4-5	4-5	5	5
Red LX		R-223	100	5-6	5	4-5	3	5	5
Blue LX			100	5-6	4-5	4-5	2-3	5	5

Fastness Test
 Light : ISO 105-B02 (3% o.w.f.) Washing: AATCC 61 1986 2A, Color Change
 Rubbing: JIS L-0849 B Chlorine: AATCC 3 1985, Color Change
 Perspiration: AATCC-15-1994, Color Change

極品化學科技股份有限公司

DYEXCEL CHEMICAL INDUSTRIAL CORPORATION

No.14, Chin-Khen 5th Rd., Kuan-Yin Industrial Zone, Tao-Yuan City, Taiwan, R.O.C.

TEL: +886-3-4836008

FAX: +886-3-4836018

dyexcel.dci@msa.hinet.net

